

Coloured Slips Batch Recipes

2 March 2026						
	%	1000	2000	3000	4000	5000
Rahu Armarrillo Slip						
310g per 250ml						
China Clay	35	350	700	1050	1400	1750
OM4 Ball Clay	25	250	500	750	1000	1250
Nepheline Syenite	33	330	660	990	1320	1650
Rahu Clay	7	70	140	210	280	350
Tin Oxide	4	40	80	120	160	200
Titanium Dioxide	8	80	160	240	320	400
Total	112	1120	2240	3360	4480	5600
Linda Arbuckle Amarillo Slip						
OM4 Ball Clay	63	630	1260	1890	2520	3150
Nepheline Syenite	32	320	640	960	1280	1600
Silica	5	50	100	150	200	250
Tin Oxide	5	50	100	150	200	250
Titanium Dioxide	10	100	200	300	400	500
Total	115	1150	2300	3450	4600	5750
Black Line						
China Clay	30					
Ball Clay	20					
Nepheline Syenite	30					
Talc	10					
Silica	10					
Black Stain	30					
Total	130					
White Line						
Ground Wadding (80 mesh)	40					
Talc	20					
China Clay	20					
Potash Feldspar	20					
Titanium Dioxide	10					
Total	110					

Jane Hamlyn's Blue						
Potash Feldspar	33.3	333	666	999	1332	1665
Cornish Stone	33.3	333	666	999	1332	1665
OM4 Ball Clay	33.3	333	666	999	1332	1665
Cobalt Carbonate	0.5	5	10	15	20	25
Total	100.4	1004	2008	3012	4016	5020
Jane Hamlyn's Blue V2						
Nepheline Syenite	62	620	1240	1860	2480	3100
OM4 Ball Clay	25	250	500	750	1000	1250
High Iron Ball Clay	13	130	260	390	520	650
Cobalt Oxide	1.5	15	30	45	60	75
For green add Titanium Dioxide	1	10	20	30	40	50
Total	102.5	1025	2050	3075	4100	5125
Green/Blue Slip						
China Clay	20	200	400	600	800	1000
OM4 Ball Clay	20	200	400	600	800	1000
Nepheline Syenite	50	500	1000	1500	2000	2500
Soda Feldspar	10	100	200	300	400	500
Chrome Oxide	1	10	20	30	40	50
Cobalt Carbonate	1.5	15	30	45	60	75
Titanium Dioxide	0.5	5	10	15	20	25
Rutile	1	10	20	30	40	50
Total	104	1040	2080	3120	4160	5200